

DESCRIPTION	MagChem 20 SC is a medium reactive magnesium oxide powder formulated for applications requiring maximum consistency in chemical, physical properties, and reactivity.																								
USES	MagChem 20 SC is used in manufacturing grain oriented steel for high performance electrical transformers, specialty ceramics, and coatings.																								
COMPOSITION (TYPICAL)	<table><thead><tr><th></th><th><u>Specifications</u></th></tr></thead><tbody><tr><td>Magnesium Oxide (MgO), %</td><td>98.00 min.</td></tr><tr><td>Calcium Oxide (CaO), %</td><td>0.60 max.</td></tr><tr><td>Silicon Dioxide (SiO₂), %</td><td>0.50 max.</td></tr><tr><td>Iron Oxide (Fe₂O₃), %</td><td>0.30 max.</td></tr><tr><td>Aluminum Oxide (Al₂O₃), %</td><td>0.20 max.</td></tr><tr><td>Chloride (Cl), %</td><td>0.03 max.</td></tr><tr><td>Sulfate (SO₄), %</td><td>0.50 max.</td></tr><tr><td>Sodium (Na), %</td><td>0.02 max.</td></tr><tr><td>Fluoride (F), %</td><td>0.03 max.</td></tr><tr><td>Boron (B), ppm</td><td>500 – 900</td></tr><tr><td>Carbon (C), %</td><td>0.20 max</td></tr></tbody></table>		<u>Specifications</u>	Magnesium Oxide (MgO), %	98.00 min.	Calcium Oxide (CaO), %	0.60 max.	Silicon Dioxide (SiO ₂), %	0.50 max.	Iron Oxide (Fe ₂ O ₃), %	0.30 max.	Aluminum Oxide (Al ₂ O ₃), %	0.20 max.	Chloride (Cl), %	0.03 max.	Sulfate (SO ₄), %	0.50 max.	Sodium (Na), %	0.02 max.	Fluoride (F), %	0.03 max.	Boron (B), ppm	500 – 900	Carbon (C), %	0.20 max
	<u>Specifications</u>																								
Magnesium Oxide (MgO), %	98.00 min.																								
Calcium Oxide (CaO), %	0.60 max.																								
Silicon Dioxide (SiO ₂), %	0.50 max.																								
Iron Oxide (Fe ₂ O ₃), %	0.30 max.																								
Aluminum Oxide (Al ₂ O ₃), %	0.20 max.																								
Chloride (Cl), %	0.03 max.																								
Sulfate (SO ₄), %	0.50 max.																								
Sodium (Na), %	0.02 max.																								
Fluoride (F), %	0.03 max.																								
Boron (B), ppm	500 – 900																								
Carbon (C), %	0.20 max																								
PHYSICAL PROPERTIES	<table><thead><tr><th></th><th><u>Specifications</u></th></tr></thead><tbody><tr><td>Loose Bulk Density, lb/ft³ (g/cm³)</td><td>12 - 30 (0.19 - 0.48)</td></tr><tr><td>Median Particle Size, micron</td><td>1.5 max.</td></tr><tr><td>BAT, seconds (range as required)</td><td>50 – 100</td></tr><tr><td>Screen Analysis:</td><td></td></tr><tr><td> % Passing 200 Mesh</td><td>99.9 min.</td></tr><tr><td> % Passing 325 Mesh</td><td>99.0 min.</td></tr><tr><td>Surface Area, m²/g</td><td>(Typical) 22</td></tr></tbody></table>		<u>Specifications</u>	Loose Bulk Density, lb/ft ³ (g/cm ³)	12 - 30 (0.19 - 0.48)	Median Particle Size, micron	1.5 max.	BAT, seconds (range as required)	50 – 100	Screen Analysis:		% Passing 200 Mesh	99.9 min.	% Passing 325 Mesh	99.0 min.	Surface Area, m ² /g	(Typical) 22								
	<u>Specifications</u>																								
Loose Bulk Density, lb/ft ³ (g/cm ³)	12 - 30 (0.19 - 0.48)																								
Median Particle Size, micron	1.5 max.																								
BAT, seconds (range as required)	50 – 100																								
Screen Analysis:																									
% Passing 200 Mesh	99.9 min.																								
% Passing 325 Mesh	99.0 min.																								
Surface Area, m ² /g	(Typical) 22																								
PACKAGING	Martin Marietta Magnesia Specialties packages these products in 50 pound bags. Please contact a sales representative for information on detailed packaging offerings and specifications.																								
STORAGE	Store in a dry place. Exposure to moisture may cause caking.																								

NOTICE: THE INFORMATION CONTAINED HEREIN IS, TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE. ANY RECOMMENDATIONS OR SUGGESTIONS MADE ARE WITHOUT WARRANTY OR GUARANTEE OF RESULTS SINCE CONDITIONS OF HANDLING AND OF USE ARE BEYOND OUR CONTROL; WE THEREFORE, ASSUME NO LIABILITY FOR LOSS OR DAMAGE INCURRED BY FOLLOWING THESE SUGGESTIONS. SELLER WARRANTS ONLY THAT THIS PRODUCT WILL MEET THE SPECIFICATIONS SET FORTH. ANY OTHER REPRESENTATION OR WARRANTY, EITHER EXPRESS OR IMPLIED, IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY. SELLERS AND MANUFACTURERS ONLY OBLIGATION SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT PROVED TO BE DEFECTIVE. BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR USERS INTENDED APPLICATION AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE IN TORT, CONTRACT OR UNDER ANY THEORY FOR ANY LOSS OR DAMAGE, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY TO USE THE PRODUCT.

Martin Marietta Magnesia Specialties, LLC

2700 Wycliff Road, Suite 320
Raleigh, North Carolina 27607 USA
Phone: (800) 648-7400
www.magnesiaspecialties.com

MagChem[®] is a trademark of
Martin Marietta Magnesia Specialties, LLC



Produced under a Quality Management System certified
to ISO 9001:2015 by PRI Certification Registrar